

## Tadiran High Power Lithium Organic Cell Model TLM-1550MP

### 1. Scope

This data sheet describes the mechanical design and performance of Tadiran high power lithium organic cell model TLM-1550MP.

### 2. Characteristics

#### 2.1. Physical

- 2.1.1. Length: 51 ±1 mm.
- 2.1.2. Diameter: 14.8 ±0.3 mm.
- 2.1.3. Weight: 20 gr. max.

#### 2.2. Electrical

##### 2.2.1. Open Circuit Voltage

(for batteries stored at RT for 1 year or less) 4.02 to 4.07 V

##### 2.2.2. Closed Circuit Voltage (at 0.1 sec) at 0.5 A load 3.88 V minimum

##### 2.2.3. Discharge

Discharge capacity at 50 mA @ RT to 2.8 V 800 mAh

Discharge capacity at 500 mA @ RT to 2.8 V 700 mAh

Maximum discharge current

Continuous to 2.8 V: 4 A

1 second pulse to 3 V: 15 A

##### 2.3. Operating Temperature range: -40 °C to 85 °C

##### 2.4. Accumulated Capacity Loss\*:


Storage Temperature	22 °C	55 °C	72 °C	85 °C
Storage Time [Y]				
1	2 %	4 %	7 %	TBD
5	5 %	15 %	28 %	N/A
10	7.5 %	22 %	N/A	N/A
15	10 %	29 %	N/A	N/A
20	12.5 %	N/A	N/A	N/A

- When tested at RT under 100 mA to 2.8 V


##### 2.5. Cell impedance: Less than 100 mOhm @ 1 kHz at room temperature.

2.6. Performance Data:


### Discharge capability at RT




### Pulse capability at RT



## Discharge capability @ 1A at several temperatures




## Pulse capability @ 1A at several temperatures



## 2.7. End of life indication:

OCV measurements can provide a good estimation for the remaining capacity of the cell as shown below:



**Capacity vs. OCV**

## Safety tests:

The cell has successfully passed the following safety tests:

- Short circuit at RT and at 55 °C.
- Oven at 150 °C.
- Impact.
- Over charge and over discharge.